

R7

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2001-311801

(43)Date of publication of application : 09.11.2001

(51)Int.Cl.

G02B 1/02
C03C 3/06
H01S 3/034

(21)Application number : 2000-131331

(71)Applicant : ASAHI GLASS CO LTD

(22)Date of filing : 28.04.2000

(72)Inventor : IKUTA YORISUKE
OKADA KANAME
KIKUKAWA SHINYA

54) SYNTHETIC QUARTZ GLASS

57)Abstract:

PROBLEM TO BE SOLVED: To provide a synthetic quartz glass excellent in vacuum UV transmittance.

SOLUTION: The synthetic quartz glass used as an optical member of an optical device using F2 laser light as a light source has $\geq 85\%$ /cm internal transmittance at 157.6 nm wavelength and \leq %/cm variation of the internal transmittance at 157.6 nm by irradiation with UV from an F2 laser, an Xe2 excimer lamp or the like.

LEGAL STATUS

Date of request for examination]

Date of sending the examiner's decision of rejection]

Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

Date of final disposal for application]

Patent number]

Date of registration]

Number of appeal against examiner's decision of rejection]

Date of requesting appeal against examiner's decision of rejection]

Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office